



7565 Industrial Court, Alpharetta, Georgia 30004
 Phone: 770-521-8666 Fax: 770-521-2299 Toll Free: 888-521-8666
www.protectivestructures.com

BULLET RESISTANT GLASS PRODUCTS				
Product	UL-752 Level	Thickness	Weight (lbs./sq. ft.)	Notes
Laminated Glass	1	1-3/16"	14.7	Thickness & weight may vary depending on application and dimensions
Laminated Glass	2	1-1/2"	19.3	
Laminated Glass	3	1-3/4"	22.46	
Laminated Glass	4	2"	25.8	
Glass Clad Polycarbonate	1	13/16"	8.4	**Differences in thickness and weight for No-Spall and Low-Spall Glass Clad Polycarbonate. Thickness & weight may vary depending on application and dimensions
Glass Clad Polycarbonate	2	1.03"	11.2	
Glass Clad Polycarbonate	3	1.22"	13.5	
Glass Clad Polycarbonate	4	1.28"	13.8	
Glass Clad Polycarbonate	5	1.28"	13.8	
Glass Clad Polycarbonate	6	1.28"	13.8	
Glass Clad Polycarbonate	7	1.04"	9.8	
Glass Clad Polycarbonate	8	2"	21.8	
Acrylic	1	1-1/4"	7.7	**Acrylic available in abrasion resistant (AR) and non AR
Acrylic	2	1-3/8"	8.5	
Acrylic / Polycarbonate	3	1-1/4"	7.7	
Polycarbonate	1	3/4"	5.1	**Polycarbonate is a non-spalling & non-richochet product
Polycarbonate	2	1"	6.5	
Polycarbonate	3	1-1/4"	8.1	
Fiberglass Panels	1	1/4"	3	**Bullet resistant fiberglass panels are opaque, generally used for armoring walls or lining courtroom benches and the like
Fiberglass Panels	2	5/16"	4.3	
Fiberglass Panels	3	7/16"	4.9	
Fiberglass Panels	4	1-3/8"	14.5	
Fiberglass Panels	5	1-7/16"	14.9	
Fiberglass Panels	6	3/8"	4	
Fiberglass Panels	7	1-1"	11.9	
Fiberglass Panels	8	1-7/16"	14.9	